



# Standard Specification for Pressure Vessel Plates, Carbon Steel, High Strength, for Moderate and Lower Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A612/A612M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification<sup>2</sup> covers killed carbon-manganese-silicon steel plates intended for welded pressure vessels in service at moderate and lower temperatures.

1.2 The maximum thickness of plates supplied under this specification is 1 in. [25 mm].

1.3 For plates produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification **A20/A20M** apply.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

### 2.1 *ASTM Standards*:<sup>3</sup>

**A20/A20M** Specification for General Requirements for Steel Plates for Pressure Vessels

**A435/A435M** Specification for Straight-Beam Ultrasonic Examination of Steel Plates

**A577/A577M** Specification for Ultrasonic Angle-Beam Examination of Steel Plates

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.11** on Steel Plates for Boilers and Pressure Vessels.

Current edition approved May 1, 2012. Published June 2012. Originally approved in 1970. Last previous edition approved in 2003 as A612/A612M – 03 (2007). DOI: 10.1520/A0612\_A0612M-12.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-612/SA-612M in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**A578/A578M** Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications

## 3. General Requirements and Ordering Information

3.1 Material supplied to this product specification shall conform to Specification **A20/A20M**. These requirements outline the testing and retesting methods and procedures, permitted variations in dimensions and mass, quality and repair of defects, marking, loading, and ordering information.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available where additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification **A20/A20M**.

3.3 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, three test results are reported for each qualifying coil. Additional requirements regarding plates from coil are described in Specification **A20/A20M**.

3.4 If the requirements of this specification are in conflict with the requirements of Specification **A20/A20M**, the requirements of this specification shall prevail.

## 4. Materials and Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification **A20/A20M**.



TABLE 1 Chemical Requirements

| Elements                      | Composition, % |
|-------------------------------|----------------|
| Carbon, max: <sup>A</sup>     |                |
| Heat analysis                 | 0.25           |
| Product analysis              | 0.29           |
| Manganese <sup>A</sup>        |                |
| Heat analysis                 | 1.00–1.50      |
| Product analysis              | 0.92–1.62      |
| Phosphorus, max: <sup>B</sup> | 0.025          |
| Sulfur, max: <sup>B</sup>     | 0.025          |
| Silicon                       |                |
| Heat analysis                 | 0.15–0.50      |
| Product analysis              | 0.13–0.55      |
| Copper, max: <sup>C</sup>     |                |
| Heat analysis                 | 0.35           |
| Product analysis              | 0.38           |
| Nickel, max: <sup>C</sup>     |                |
| Heat analysis                 | 0.25           |
| Product analysis              | 0.28           |
| Chromium, max: <sup>C</sup>   |                |
| Heat analysis                 | 0.25           |
| Product analysis              | 0.29           |
| Molybdenum, max: <sup>C</sup> |                |
| Heat analysis                 | 0.08           |
| Product analysis              | 0.09           |
| Vanadium, max: <sup>C</sup>   |                |
| Heat analysis                 | 0.08           |
| Product analysis              | 0.09           |

<sup>A</sup> For each reduction of 0.01 percentage point below the specified carbon maximum, an increase of 0.06 percentage point manganese above the specified maximum is permitted up to a maximum of 1.65 % for heat analysis (1.70 % for product analysis).

<sup>B</sup> Applies to both heat and product analyses.

<sup>C</sup> When analysis shows that the amount of an element is 0.02 % or lower, the value may be reported as ≤0.02 %.

TABLE 2 Tensile Requirements

|                                                   | Thickness                   |                                            |
|---------------------------------------------------|-----------------------------|--------------------------------------------|
|                                                   | 0.5 in. [12.5 mm] and Under | Over 0.5 in. to 1 in. [Over 12.5 to 25 mm] |
| Tensile strength, ksi [MPa]                       | 83–105 [570–725]            | 81–101 [560–695]                           |
| Yield strength, min, <sup>A</sup> ksi [MPa]       | 50 [345]                    | 50 [345]                                   |
| Elongation in 8 in. [200 mm], min, % <sup>B</sup> | 16                          | 16                                         |
| Elongation in 2 in. [50 mm], min, % <sup>B</sup>  | 22                          | 22                                         |

<sup>A</sup> Determined by either the 0.2 % offset method or the 0.5 % extension-under-load method.

<sup>B</sup> See Specification A20/A20M for elongation adjustments.

## 5. Heat Treatment

5.1 Plates are normally supplied in the as-rolled condition. Plates may be ordered normalized or stress relieved, or both.

## 6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition given in Table 1 unless otherwise modified in accordance with Supplementary Requirement S17, Vacuum Carbon-Deoxidized Steel, in Specification A20/A20M.

## 7. Mechanical Properties

7.1 *Tension Test*—The plates, as represented by the tension test specimens, shall conform to the requirements given in Table 2.

## 8. Keywords

8.1 carbon steel; steel plates for pressure vessels; lower temperature service; high strength steel plates



## SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order.

A list of standardized supplementary requirements for use at the option of the purchaser are included in Specification **A20/A20M**. Those that are considered suitable for use with this specification are listed by title.

- |                                                                              |                                                                                      |
|------------------------------------------------------------------------------|--------------------------------------------------------------------------------------|
| S1. Vacuum Treatment,                                                        | S8. Ultrasonic Examination in accordance with Specification <b>A435/A435M</b> ,      |
| S2. Product Analysis,                                                        | S9. Magnetic Particle Examination,                                                   |
| S3. Simulated Post-Weld Heat Treatment of Test Coupons,                      | S11. Ultrasonic Examination in accordance with Specification <b>A577/A577M</b> ,     |
| S4.1 Additional Tension Test,                                                | S12. Ultrasonic Examination in accordance with Specification <b>A578/A578M</b> , and |
| S5. Charpy V-Notch Impact Test,                                              | S17. Vacuum Carbon-Deoxidized Steel.                                                 |
| S6. Drop Weight Test (for Material 0.625 in. [16 mm] and over in Thickness), |                                                                                      |
| S7. High Temperature Tension Test,                                           |                                                                                      |

## SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A612/A612M – 03 (2007)) that may impact the use of this standard. (Approved May 1, 2012.)

- |                                               |                                 |
|-----------------------------------------------|---------------------------------|
| (1) <b>Table 1</b> was revised.               | (3) Section <b>8</b> was added. |
| (2) Section <b>3</b> was editorially revised. |                                 |

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*